



**PPI Adhesive Products Limited**

Waterford Industrial Estate  
Cork Road  
Waterford, Ireland.  
Phone: +353 (0) 51 590400  
Fax: +353 (0) 51 377687  
Email: info@ppi.ie  
Internet: www.ppi.ie



# PPI – PRODUCT INFORMATION

## RD-514-C WHITE POLYIMIDE LABELSTOCK FOR THERMAL TRANSFER PRINTING

**Description:**

RD-514-C is a high temperature thermal transfer printable labelstock. Designed to be printed with high performance resin based ribbons, RD-514-C will withstand temperatures up to 300°C and is resistant against many solvents and processing chemicals.

**Applications**

Electronic Industry: For underside of printed circuit boards and in surface mount applications.  
Automotive Industry  
Aerospace Industry  
Metal processing  
General Industrial applications requiring high temperature resistance and/or chemical resistance.

**Properties**

- Thermal transfer printing
- Suitable for barcode printing
- Smudge resistant

RD-514-C will withstand high temperatures including direct contact with molten solder. RD-514-C is UL 510 Flame Retardant.

**Resistance against Chemicals & Solvents**

**Test Method:** Labelstock is applied to stainless steel plate and immersed in medium.

Medium	Test Duration	Result
Water at 95°C	8 hours	No effect*
Transformer oil at 23°C	24 hours	No effect*
Diesel oil at 23°C	24 hours	No effect*
Motor oil (SAE 30) at 23°C	24 hours	No effect*
Hydraulic oil (G.M Dextron II) at 23°C	24 hours	No effect*
Hexane at 23°C	24 hours	No effect*
Heptane at 23°C	16 hours	No effect*
White Spirit at 23°C	1 hour	No effect*
Jet Fuel A1 (ASTM D1655) at 23°C	24 hours	No effect*
Avgas 100LL (ASTM D910) at 23°C	24 hours	No effect*
Anti-Freeze solution at 23°C* <sup>1</sup>	24 hours	No effect*
Detergent solution at 23°C* <sup>2</sup>	8 hours	No effect*

\* ADHESION TO TEST PLATE IS UNAFFECTED/SURFACE IS INTACT

\*<sup>1</sup> MIXTURE OF ETHYLENE GLYCOL AND WATER (1:1)

\*<sup>2</sup> WATER WITH 3% COMMERCIAL DETERGENT/ SURFACTANT

Recommended ribbons & printers	
Printer	Recommended Ribbons
<b>Fargo Prodigy Plus</b> (203 dots/inch, 4 inch/sec speed, high burn setting)	Armor AXR +7, AXR +8, AXR +9. Brady R4300, R4900, R6000, R6002. Sony TR-4070- EA, 4075, 6075. Ricoh B-110A, B-110C, B-110CR, B-120E.
<b>Zebra 90 Xi</b> (300 dot/inch, 2 inch/sec speed, high burn setting)	Armor AXR +7, AXR +8, AXR +9. Brady R4300, R4900, R6000, R6002. Sony TR-4070- EA, 4075, 6075. Ricoh B-110A, B-110C, B-110CR, B-120E.
<b>Zebra 91</b> (300 dot/inch, 2 inch/sec speed, high burn setting)	Armor AXR +7, AXR +8, AXR +9. Brady R4300, R4900, R6000, R6002. Sony TR-4070- EA, 4075, 6075. Ricoh B-110A, B-110C, B-110CR, B-120E.

**Note:** Above recommendations are based on tests with ribbons as supplied by Manufacturer. No guarantee is given in respect of performance of own branded ribbons or re-formulated versions of the above ribbons. For Printed Circuit Board labeling applications, we recommend that the user evaluates compatibility of ribbon ink with flux employed during soldering operations.

Rev.3/ 16 July 15

**PPI Adhesive Products Limited**

Waterford Industrial Estate  
 Cork Road  
 Waterford, Ireland.  
 Phone: +353 (0) 51 590400  
 Fax: +353 (0) 51 377687  
 Email: info@ppi.ie  
 Internet: www.ppi.ie



# PPI – PRODUCT INFORMATION

## RD-514-C WHITE POLYIMIDE LABELSTOCK FOR THERMAL TRANSFER PRINTING.

Technical Data	EN Value	ASTM Value
<b>Supporting base:</b>	Polyimide film	
<b>Base thickness:</b>	0.025 mm	1.0 Mil
<b>+/- 0.003 mm</b>	0.050 mm	2.0 Mil
<b>Total thickness:</b>	0.075 mm	3.0 Mil
<b>+/- 0.005 mm</b>	0.100 mm	4.0 Mil
<b>Adhesive:</b>	Acrylic	
<b>Colour:</b>	White	
<b>Short term heat resistance:</b>	Up to 300°C	
<b>Interliner</b>	Siliconised paper NS I-91	
<b>Liner Thickness:</b>	0.075 mm +/- 0.006 mm	
<b>Liner Area weight:</b>	91 +/- 4 g/m <sup>2</sup>	

Additional Information
<b>Minimum recommended application temperature :</b> Room Temperature: 18°C (64°F)
<b>Printing method:</b> Thermal Transfer.
<b>Die cutting:</b> Rotary die-cutting is recommended. High winding tensions should be avoided.
<b>Packaging:</b> Store roll labelstock and finished labels in plastic bags.
<b>Handling:</b> Avoid contact with label surface. Processing environment should be kept clean and free from dust and dirt.
<b>Storage Conditions:</b> Recommended storage conditions are 20°C (68°F) and 50% relative humidity

Adhesive Strength: 180° Peel, 10 min Dwell		
Surface	EN Value	ASTM Value
Stainless Steel	2.5 N/ cm + 0.5 N/cm - 0.8 N/cm	22.5 OZ/INCH
Aluminium	3.0 N/cm	27.0 OZ/INCH
Solder resist coated Printed Circuit Board	1.5 N/ cm	13.5 OZ/INCH
Polyimide Film	2.0 N/ cm	18.0 OZ/INCH
Powder Coated Surface	2.5 N/ cm	22.5 OZ/INCH

Heat Resistance	
Temperature	Time
300°C (572°F)	15 minutes
250°C (482°F)	90 minutes
200°C (392°F)	240 hours

\*Test according to ASTM D-1000/04, Section 46-53

All statements, technical data and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties, express or implied.

Seller's and manufacturer's only obligation shall be to replace such quantity of the product is proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use or the inability to use the product. Before using, users shall determine the suitability of the product for their initial use, and users assume all risk and liability whatsoever in connection with them.

No statement or recommendation not contained herein shall have any force or effect unless embodied in a written agreement signed by authorized officers of seller and manufacturer.

Rev.3/ 16 July 15